

Cover	Standard & Grade	Min. Tensile Strength (Mpa)	Min. Elongation at Break %	Min. Swelling in Fuel B (%)	Application
High Oil Resistant	HOR	15	350	40	Oil Based Fertilizers
Regular Oil Resistant	ROR	15	350	70	Tar, Crude Petroleum products, etc
Medium Oil Resistant	MOR	15	350	110	Vegetable Oils and Animal Greases
Heat & Oil Resistant	HROR	15	350	55	Hot Asphalt (125°C)
Fire and Oil Resistant	FROR	15	350	65	Uses in installations which are prone to fires